PIETBOON

TWILL

FABRICS **P2**

FEATURES

Composition	63% Cotton, 37% Polyester
Width	140 cm
Weight	703 g/lm
Abrasion	43.000 martindale
Colour fastness	4 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
CAL TB 117 test	Fail
BS 5852 0	Pass
BS 5852 1	Fail
DIN EN ISO 1021 PART I	Fail
DIN EN ISO 1021 PART II	Fail
NFPA 260	Fail

SAMPLES



TWILL 2


TWILL 48



TWILL 63



TWILL 49


TWILL 3


TWILL 23


TWILL 52


TWILL 5


TWILL 1

PIETBOON

WEAVE

FABRICS **P2**


FEATURES


Composition	70% Viscose, 30% Linen
Width	140 cm
Weight	869 g/lm
Abrasion	25.000 martindale
Colour fastness	4-5 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
CAL TB 117 test	Fail
BS 5852 0	Pass
BS 5852 1	Pass
DIN EN ISO 1021 PART I	Fail
DIN EN ISO 1021 PART II	Fail
NFPA 260	Fail


SAMPLES



WEAVE 19



WEAVE 40


WEAVE 1


WEAVE 17



WEAVE 303



WEAVE 301



WEAVE 22


WEAVE 20


WEAVE 216


WEAVE 16


WEAVE 21


WEAVE 302

PIETBOON

BIRCH

FABRICS **P2**


FEATURES

Composition	33% polyester, 25% polyacrylic, 23% viscose, 10% cotton, 9% linen
Width	140 cm
Weight	884 g/lm
Abrasion	50.000 martindale
Colour fastness	5/6 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
CAL TB 117 test	Pass
BS 5852 0	Pass
BS 5852 1	Fail
DIN EN ISO 1021 PART I	Fail
DIN EN ISO 1021 PART II	Fail
NFPA 260	Fail

SAMPLES




BIRCH 5



BIRCH 16



BIRCH 11



BIRCH 17



BIRCH 21

PIETBOON


BRESCIA

FABRICS **P2**

FEATURES

Composition	42% Viscose, 38% Cotton, 14% Polyacrylic, 6% Polyester
Width	140 cm
Weight	1008 g/lm
Abrasion	30.000 martindale
Colour fastness	4/5 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
CAL TB 117 test	Pass
BS 5852 0	Pass
BS 5852 1	Pass
DIN EN ISO 1021 PART I	Fail
DIN EN ISO 1021 PART II	Fail
NFPA 260	Pass

SAMPLES




BRESCIA 12




BRESCIA 11



BRESCIA 10



BRESCIA 8



BRESCIA 7



BRESCIA 6



BRESCIA 5



BRESCIA 4



BRESCIA 3



BRESCIA 1

PIETBOON

CANVAS

FABRICS **P2**

FEATURES

Composition	34% Viscose, 31% Cotton, 15% Linen, 13% Polyacrylic, 7% Polyethylene
Width	140 cm
Weight	945 g/lm
Abrasion	25.000 martindale
Colour fastness	4/5 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
CAL TB 117 test	Pass
BS 5852 0	Pass
BS 5852 1	Pass
DIN EN ISO 1021 PART I	Fail
DIN EN ISO 1021 PART II	Fail
NFPA 260	Fail

SAMPLES




CANVAS 3




CANVAS 16




CANVAS 2



CANVAS 4



CANVAS 6



CANVAS 7

PIETBOON

CIRRUS

FABRICS **P1**

FEATURES

Composition	32% Viscose, 25% Acrylic, 15% Linen, 15% Polyester, 13% Cotton
Width	140 cm
Weight	710 g/lm
Abrasion	25.000 martindale
Colour fastness	ISO 4-5 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
CAL TB 117 test	Pass
BS 5852 0	Pass

SAMPLES



CIRRUS 01-08



CIRRUS 02-04



CIRRUS 03-05



CIRRUS 04-16



CIRRUS 05-10



CIRRUS 06-22



CIRRUS 07-06



CIRRUS 08-24



CIRRUS 09-07



CIRRUS 10-19



CIRRUS 11-12



CIRRUS 12-13

PIETBOON

COBBLE

FABRICS **P3**

FEATURES

Composition	29% Acrylic, 25% Virgin Wool, 13% Polyester, 12% Cotton, 11% Viscose, 10% Linen
Width	140 cm
Weight	918 g/lm
Abrasion	50.000 martindale
Colour fastness	ISO 4-5 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
CAL TB 117 test	Pass
BS 5852 0	Pass
BS 5852 1	Pass

SAMPLES



COBBLE 01-01



COBBLE 02-11



COBBLE 03-43



COBBLE 04-44



COBBLE 05-05



COBBLE 06-45



COBBLE 07-41



COBBLE 08-30



COBBLE 09-06

PIETBOON

COBBLE

FABRICS **P3**

SAMPLES



COTTONS 28



COTTONS 12



COTTONS 59



COTTONS 36

COTTONS 67



COTTONS 23

PIETBOON


COTTONS

FABRICS **P1**

FEATURES

Composition	100% Cotton
Width	140 cm
Abrasion	65.000 martindale
Colour fastness	5(1-8) Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
CAL TB 117 test	Pass
BS 5852 0	Pass
BS 5852 1	Fail/Pass with after treatment
DIN EN ISO 1021 PART I	Pass
DIN EN ISO 1021 PART II	Fail
NFPA 260	Pass

SAMPLES



COTTONS 54



COTTONS 11




COTTONS 16



COTTONS 58



COTTONS 21



COTTONS 07




COTTONS 25



COTTONS 60



COTTONS 40



COTTONS 19



COTTONS 18



COTTONS 65

PIETBOON

COTTONS

FABRICS **P1**

SAMPLES



COTTONS 28




COTTONS 12



COTTONS 59



COTTONS 36



COTTONS 67



COTTONS 23

PIETBOON

FLAX

FABRICS **P3**


FEATURES

Composition	59% Linen, 18% Cotton, 15% Viscose, 8% Polyester
Width	140 cm
Abrasion	40.000 martindale
Colour fastness	5/6 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
CAL TB 117 test	Fail
BS 5852 0	Pass
BS 5852 1	Pass
DIN EN ISO 1021 PART I	Fail
DIN EN ISO 1021 PART II	Fail
NFPA 260	Fail


SAMPLES




FLAX 1




FLAX 8




FLAX 10



FLAX 6



FLAX 9



FLAX 2



FLAX 3

PIETBOON

FLOCK

FABRICS **P2**

FEATURES

Composition	35% Wool, 35% polyacrylic, 23% polyester, 7% cotton
Width	140 cm
Weight	587 g/lm
Abrasion	40.000 martindale
Colour fastness	4/5 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
CAL TB 117 test	Pass
BS 5852 0	Pass
BS 5852 1	Fail
DIN EN ISO 1021 PART I	Fail
DIN EN ISO 1021 PART II	Fail
NFPA 260	Fail


SAMPLES


FLOCK 02


FLOCK 03


FLOCK 04


FLOCK 05


FLOCK 06


FLOCK 18


FLOCK 10


FLOCK 11


FLOCK 12


FLOCK 13


FLOCK 17

PIETBOON


GEM

FABRICS **P4**

FEATURES

Composition	42% Cotton, 30% Wool, 28% Lyocell
Width	140 cm
Abrasion	45.000 martindale
Colour fastness	5 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
CAL TB 117 test	Fail
BS 5852 0	Pass
BS 5852 1	Pass
DIN EN ISO 1021 PART I	Fail
DIN EN ISO 1021 PART II	Fail

SAMPLES




GEM 0123




GEM 0230



GEM 0322



GEM 0416



GEM 0512



GEM 0626



GEM 0706



GEM 0813



GEM 0901



GEM 1005



GEM 1103



GEM 1204

PIETBOON

GEM

FABRICS **P4**


SAMPLES



GEM 1314




GEM 1409




GEM 1518



GEM 1615



GEM 1727



GEM 1819



GEM 1920

PIETBOON

GRAVEL

FABRICS **P3**

FEATURES

Composition	30% Polyester, 28% Acrylic, 21% Viscose, 12% Cotton, 9% Linen
Width	140 cm
Abrasion	40.000 martindale
Colour fastness	5-6 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
CAL TB 117 test	Pass
BS 5852 0	Pass
BS 5852 1	Fail
DIN EN ISO 1021 PART I	Pass
DIN EN ISO 1021 PART II	Fail

SAMPLES



GRAVEL 0103



GRAVEL 0228



GRAVEL 0317



GRAVEL 0439



GRAVEL 0526



GRAVEL 0615



GRAVEL 0711



GRAVEL 0804

PIETBOON

GRAVEL

FABRICS **P2**

SAMPLES



GRAVEL 0902



GRAVEL 1036



GRAVEL 1120



GRAVEL 1231



GRAVEL 13100

PIETBOON

HUSK

FABRICS **P2**

FEATURES

Composition	34% Viscose, 31% Cotton, 15% Linen, 13% Acrylic, 7% Polyester
Width	140 cm
Weight	587 g/lm
Abrasion	30.000 martindale
Colour fastness	ISO 4-5 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
BS 5852 0	Pass
BS 5852 1	Pass

SAMPLES



HUSK 01-15



HUSK 02-06



HUSK 03-27



HUSK 04-151




HUSK 05-150



HUSK 06-46



HUSK 07-16



HUSK 08-13



HUSK 09-10



HUSK 10-07



HUSK 11-12

PIETBOON

MOSS

FABRICS **P3**

FEATURES

Composition	22% Acrylic, 22% Virgin Wool, 22% Polyester, 14% Viscose, 13% Cotton, 7% Linen
Width	140 cm
Weight	810 g/lm
Abrasion	30.000 martindale
Colour fastness	ISO 4-5 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
CAL TB 117 test	Pass
BS 5852 0	Pass
BS 5852 1	Fail

SAMPLES



MOSS 01



MOSS 02



MOSS 04



MOSS 09



MOSS 08



MOSS 10



MOSS 12



MOSS 13



MOSS 05



MOSS 06



MOSS 07

PIETBOON

OXFORD

FABRICS **P3**

FEATURES

Composition	39% Linen, 27% Jute, 24% Viscose, 10% Cotton
Width	140 cm
Weight	1000 g/lm
Abrasion	30.000 martindale
Colour fastness	4 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
CAL TB 117 test	Fail
BS 5852 0	Pass
BS 5852 1	Pass
DIN EN ISO 1021 PART I	Fail
DIN EN ISO 1021 PART II	Fail
NFPA 260	Fail

SAMPLES



OXFORD 2



OXFORD 27



OXFORD 4



OXFORD 55




OXFORD 58



OXFORD 28



OXFORD 54



OXFORD 18

PIETBOON

SALAR

FABRICS **P3**

FEATURES

Composition	55% Viscose, 25% Linen, 9% Cotton, 6% Polyester, 4% Acrylic, 1% Polyamide
Width	140 cm
Weight	1070 g/lm
Abrasion	80.000 martindale
Colour fastness	ISO 4-5 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
BS 5852 0	Pass
BS 5852 1	Pass

SAMPLES



SALAR 02



SALAR 22



SALAR 01



SALAR 04



SALAR 14



SALAR 08



SALAR 05



SALAR 16

PIETBOON

TABBY

FABRICS **P1**


FEATURES


Composition	70% Viscose, 30% Linen
Width	140 cm
Weight	635g/lm
Abrasion	20.000 martindale
Colour fastness	4/5 Dep. on colour
Cleaning	Dry cleaning or visit www.pietboon-care.nl
CAL TB 117 test	Fail
BS 5852 0	Pass
BS 5852 1	Fail
DIN EN ISO 1021 PART I	Fail
DIN EN ISO 1021 PART II	Fail
NFPA 260	Fail

SAMPLES



TABBY 1



TABBY 2


TABBY 4


TABBY 6



TABBY 7


TABBY 9


TABBY 11


TABBY 12


TABBY 16









TABBY 18

PIETBOON

STORM

HIGH PERFORMANCE FABRICS

FEATURES

NR.	01-8	02-58, 03-53	04-8, 05-13	06-81	07-47	08-3906, 10-3705, 12-3758	09-24	11-75
COMPOSITION	97% PP 3% PL	83% PP 17% PL	88% PP 12% PL	83% PP 17% PL	88% PP 12% PL	100% PC	100% PP	83% PP 17% PL
WIDTH	140	140	140	140	140	140	140	140
WEIGHT	900 G/LM	460 G/LM	648 G/LM	500 G/LM	658 G/LM	356 G/LM	1022 G/LM	470 G/LM
ABRASION (MARTINDALE)	50.000	30.000	30.000	25.000	30.000	30.000	100.000	40.000
COLOUR FASTNESS	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5
CLEANING FOR MORE DETAILS: pietboon-care.nl								
CALL TB 117	PASS	PASS	PASS	PASS	PASS	PASS	PASS	PASS
BS 5852 0	PASS	PASS	PASS	PASS	PASS	FAIL	PASS	PASS
BS 5852 1	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL
DIN EN ISO PART I	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL
DIN EN ISO PART II	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL
NFPA 260	FAIL	FAIL	FAIL	FAIL	FAIL	PASS	FAIL	FAIL
WATER REPELLENT	NO	NO	NO	NO	NO	YES	NO	NO

ALL THE HIGH PERFORMANCE FABRICS ARE WATER RESISTANT

SAMPLES



STORM
01-8 **P3**



STORM
02-58 **P1**



STORM
03-53 **P1**



STORM
04-8 **P3**



STORM
05-13 **P3**



STORM
06-81**P2**



STORM
07-47 **P3**



STORM
08-3906 **P2**



STORM
09-24 **P3**



STORM
10-3705 **P2**

PIETBOON

STORM

HIGH PERFORMANCE FABRICS

SAMPLES



STORM
11-75 **P1**



STORM
12-3758 **P2**

PIETBOON

BLOOM

HIGH PERFOMANCE FABRICS **P3**

FEATURES

COMPOSITION	54% POLYACRYLIC, 46% POLYESTER
WIDTH	140 CM
WEIGHT	740 G/LM
ABRASION	100.000 MARTINDALE
COLOUR FASTNESS	4/5 DEPENTS ON COLOUR
CLEANING	 OR VISIT pietboon-care.nl
CAL TB 117 TEST	FAIL
BS 5852 0	FAIL
BS 5852 1	FAIL
DIN EN ISO 1021 PART I	FAIL
DIN EN ISO 1021 PART II	FAIL
NFPA 260	FAIL
WATER REPELLENT	YES

SAMPLES


BLOOM 01-407


BLOOM 02-413


BLOOM 01-405


BLOOM 03-404


BLOOM 04-406


BLOOM 05-403


BLOOM 06-411


BLOOM 07-410


BLOOM 08-409


BLOOM 09-408


BLOOM 10-402


BLOOM 11-401


BLOOM 12-412

PIETBOON

CLIFF


HIGH PERFORMANCE FABRICS

FEATURES

NR.	01-10029	02-3471490	03-62140	04-5 07-11	05-43	06-71 08-82	11-77	12-3729 14-3792137	13-3729
COMPOSITION	100% PC	100% PC	98% PC 2% AF	88% PP 12% PL	88% PP 12% PL	83% PP 17% PL	83% PP 17% PL	100% PC	100% PC
WIDTH	140	140	140	140	140	140	140	140	140
WEIGHT	385 G/LM	844 G/LM	756 G/LM	648 G/LM	658 G/LM	500 G/LM	470 G/LM	356 G/LM	469 G/LM
ABRASION (MARTINDALE)	30.000	30.000	37.000	30.000	30.000	25.000	40.000	30.000	26.000
COLOUR FASTNESS	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5
CLEANING	DRY CLEANING	DRY CLEANING	DRY CLEANING	DRY CLEANING	DRY CLEANING	DRY CLEANING	DRY CLEANING	DRY CLEANING	DRY CLEANING
CALL TB 117	FAIL	PASS	PASS	PASS	PASS	PASS	PASS	PASS	PASS
BS 5852 0	FAIL	FAIL	FAIL	PASS	PASS	PASS	PASS	FAIL	FAIL
BS 5852 1	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL
DIN EN ISO PART I	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL
DIN EN ISO PART II	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL
NFPA 260	PASS	PASS	PASS	FAIL	FAIL	FAIL	FAIL	PASS	PASS
WATER REPELLENT	PASS	PASS	PASS	FAIL	FAIL	FAIL	FAIL	PASS	PASS

ALL THE HIGH PERFORMANCE FABRICS ARE WATER RESISTANT


SAMPLES



CLIFF
01-10029 **P2**



CLIFF
02-347140 **P3**



CLIFF
03-62140 **P3**




CLIFF
04-5 **P3**



CLIFF
05-43 **P3**



CLIFF
06-71 **P2**




CLIFF
07-11 **P3**



CLIFF
08-82 **P2**



CLIFF
11-77 **P1**




CLIFF
12-3729 **P2**

PIETBOON


CLIFF

HIGH PERFORMANCE FABRICS

SAMPLES



CLIFF
13-3729 **P3**



CLIFF
14-3792137 **P2**

PIETBOON

FOREST

HIGH PERFORMANCE FABRICS

FEATURES

NR.	01-01 03-05, 05-04, 07-03, 09-10, 11-09, 13-11, 15-02	02-17, 04-271, 06-272, 08-02, 10-276, 12-273, 14-274, 16-1000
COMPOSITION	100% PC	100% PC
WIDTH	140	140
WEIGHT	1080 G/LM	614 G/LM
ABRASION (MARTINDALE)	40.000	35.000
COLOUR FASTNESS	ISO 4-5	ISO 4-5
CLEANING FOR MORE DETAILS: pietboon-care.nl		
CALL TB 117	FAIL	PASS
BS 5852 0	FAIL	PASS
BS 5852 1	FAIL	PASS
DIN EN ISO PART I	FAIL	FAIL
DIN EN ISO PART II	FAIL	FAIL
NFPA 260	FAIL	FAIL
WATER REPELLENT	NO	NO

ALL THE HIGH PERFORMANCE FABRICS ARE WATER RESISTANT

SAMPLES



FOREST
01-01 **P3**



FOREST
02-17 **P2**



FOREST
03-05 **P3**



FOREST
04-271 **P2**



FOREST
05-04 **P3**



FOREST
06-272 **P2**



FOREST
07-03 **P3**



FOREST
08-02 **P2**



FOREST
09-10 **P3**



FOREST
10-276 **P2**

PIETBOON

FOREST

HIGH PERFORMANCE FABRICS

SAMPLES



FOREST
11-09 **P3**



FOREST
12-273 **P2**



FOREST
13-11 **P3**



FOREST
14-274 **P2**



FOREST
15-02 **P3**






FOREST
16-1000 **P2**

PIETBOON

MIST

HIGH PERFORMANCE FABRICS

FEATURES

NR.	01-40	02-80 07-82 10-76	03-5	04-77	05-3741	06-52	08-6	09-59140
COMPOSITION	88% PP 12% PL	83% PP 17% PL	97% PP 3% PL	83% PP 17% PL	100% PC	83% PP 17% PL	88% PP 12% PL	98% PC 2% AF
WIDTH	140	140	140	140	140	140	140	140
WEIGHT	658 G/LM	470 G/LM	900 G/LM	500 G/LM	356 G/LM	460 G/LM	648 G/LM	756 G/LM
ABRASION (MARTINDALE)	30.000	40.000	50.000	25.000	30.000	30.000	30.000	37.000
COLOUR FASTNESS	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5
CLEANING FOR MORE DETAILS: pietboon-care.nl								
CALL TB 117	PASS	PASS	PASS	PASS	PASS	PASS	PASS	PASS
BS 5852 0	PASS	PASS	PASS	PASS	FAIL	PASS	PASS	FAIL
BS 5852 1	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL
DIN EN ISO PART I	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL
DIN EN ISO PART II	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL
NFPA 260	FAIL	FAIL	FAIL	FAIL	PASS	FAIL	FAIL	PASS
WATER REPELLENT	NO	NO	NO	NO	YES	NO	NO	YES

ALL THE HIGH PERFORMANCE FABRICS ARE WATER RESISTANT

SAMPLES



MIST
01-40 **P3**



MIST
02-80 **P1**



MIST
03-5 **P3**



MIST
04-77 **P2**



MIST
05-3741 **P2**



MIST
06-52 **P1**



MIST
07-82 **P1**



MIST
08-6 **P3**



MIST
09-59140 **P3**






MIST
10-76 **P1**

PIETBOON

NORTH SEA

HIGH PERFORMANCE FABRICS

FEATURES

NR.	01-3706 10-3737	02-55 11-61	03-3	04-3	05-65140, 06-69140	07-344140	08-81	09-23 13-22	12-4	14-10059
COMPOSITION	100% PC	83% PP 17% PL	88% PP 12% PL	88% PP 12% PL	98% PC 2% AF	100% PC	83% PP 17% PL	100% PP	97% PP 3% PL	100% PC
WIDTH	140	140	140	140	140	140	140	140	140	140
WEIGHT	356 G/LM	460 G/LM	658 G/LM	648 G/LM	756 G/LM	844 G/LM	470 G/LM	1.022 G/LM	900 G/LM	385 G/LM
ABRASION (MARTINDALE)	30.000	30.000	30.000	30.000	37.000	30.000	40.000	100.000	50.000	30.000
COLOUR FASTNESS	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5	ISO 4-5
CLEANING FOR MORE DETAILS: pietboon-care.nl										
CALL TB 117	PASS	PASS	PASS	PASS	PASS	PASS	PASS	PASS	PASS	FAIL
BS 5852 0	FAIL	PASS	PASS	PASS	FAIL	FAIL	PASS	PASS	PASS	FAIL
BS 5852 1	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL
DIN EN ISO PART I	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL
DIN EN ISO PART II	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL	FAIL
NFPA 260	PASS	FAIL	FAIL	FAIL	PASS	PASS	FAIL	FAIL	FAIL	PASS
WATER REPELLENT	YES	NO	NO	NO	YES	YES	NO	NO	NO	YES

ALL THE HIGH PERFORMANCE FABRICS ARE WATER RESISTANT

SAMPLES



NORTH SEA
01-3706 **P2**



NORTH SEA
02-55 **P1**



NORTH SEA
03-3 **P3**



NORTH SEA
04-3 **P3**



NORTH SEA
05-65140 **P3**



NORTH SEA
06-69140 **P3**



NORTH SEA
07-344140 **P3**



NORTH SEA
08-81 **P1**



NORTH SEA
09-23 **P3**



NORTH SEA
10-3737 **P2**

PIETBOON

NORTH SEA

HIGH PERFORMANCE FABRICS

SAMPLES



NORTH SEA
11-61 **P1**



NORTH SEA
12-4 **P3**



NORTH SEA
13-22 **P3**



NORTH SEA
14-10059 **P2**